



Spacemagnets Europe GmbH

Spacemagnets Serve the World

N54

Sintered NdFeB-Magnets


A neodymium magnet (also known as NdFeB, NIB or Neo magnet), the most widely used type of rare-earth magnet, is a permanent magnet made from an alloy of neodymium, iron and boron to form the Nd₂Fe₁₄B tetragonal crystalline structure. NdFeB-magnets are the strongest type of permanent magnet commercially available.

Magnetic Properties	Characteristic	Unit	Min	Nominal	Max
	Br Residual Induction		Gauss	14500	14750
		mT	1450	1475	1500
Hcb Coercivity		Oersteds	9000		
		KA/M	716		
Hcj Intrinsic Coercivity		Oersteds	11000		
		KA/M	876		
BHmax Maximum Energy Product		MGOe	52	54	56
		KJ/M ³	414	430	446

Thermal Properties	Characteristic	Unit	C//	C⊥
	Reversible Temperature Coefficients ⁽¹⁾			
Of Induction, α (Br)		%/°C		-0.12
Of Coercivity, β (Hcj)		%/°C		-0.750
Coefficient of Thermal Expansion ⁽²⁾		$\Delta L/L$ per °C $\times 10^{-6}$	7.5	-0.1
Thermal Conductivity		kcal/mhr°C	7.6	5.8
Specific Heat ⁽³⁾		cal/g°C		0.11
Curie Temperature, Tc		°C		310
Other Properties	Flexural Strength	psi		41300
		Mpa		285
	Density	g/cm ³		7.6
	Hardness, Vickers	Hv		620
	Electrical Resistivity	$\mu\Omega \cdot \text{cm}$		180

Notes: (1) Coefficients measured between 20 and 80 °C
 (2) Between 20 and 180 °C (3) Between 20 and 140 °C

Material: N54



1KA/M = 12.566 Oe 1Koe = 79,577 KA/M 10KGs = 1 Tesla

Notes: The material data and demagnetization curves shown above represent typical properties that may vary due to product shape and size.
 Demagnetization curves show nominal Br and minimum Hcj.
 Magnets can be supplied thermal stabilized or magnetically calibrated to customer specifications.
 Additional grades are available, Please contact the factory for information.