



Spacemagnets Europe GmbH

Spacemagnets Serve the World

N-45H

Sintered NdFeB-Magnets


A neodymium magnet (also known as NdFeB, NIB or Neo magnet), the most widely used type of rare-earth magnet, is a permanent magnet made from an alloy of neodymium, iron and boron to form the Nd₂Fe₁₄B tetragonal crystalline structure. NdFeB-magnets are the strongest type of permanent magnet commercially available.

Magnetic Properties	Characteristic	Unit	Min	Nominal	Max
	Br Residual Induction		Gauss	13200	13400
		mT	1320	1340	1360
Hcb Coercivity		Oersteds	12100		
		KA/M	963		
Hcj Intrinsic Coercivity		Oersteds	17000		
		KA/M	1353		
BHmax Maximum Energy Product		MGOe	43	44.5	46
		KJ/M ³	342	354	366

Thermal Properties	Characteristic	Unit	C//	C⊥
	Reversible Temperature Coefficients ⁽¹⁾			
Of Induction, α (Br)		%/°C		-0.12
Of Coercivity, β (Hcj)		%/°C		-0.605
Coefficient of Thermal Expansion ⁽²⁾		$\Delta L/L$ per °C $\times 10^{-6}$	7.5	-0.1
Thermal Conductivity		kcal/mhr°C	7.6	5.8
Specific Heat ⁽³⁾		cal/g°C		0.11
Curie Temperature, Tc		°C		310
Other Properties	Flexural Strength	psi		41300
		Mpa		285
	Density	g/cm ³		7.6
	Hardness, Vickers	Hv		620
	Electrical Resistivity	$\mu\Omega \cdot \text{cm}$		180

Notes: (1) Coefficients measured between 20 and 180 °C
 (2) Between 20 and 180 °C (3) Between 20 and 140 °C

Material: N-45H



1KA/M = 12.566 Oe 1Koe = 79,577 KA/M 10KGs = 1 Tesla

Notes: The material data and demagnetization curves shown above represent typical properties that may vary due to product shape and size.
 Demagnetization curves show nominal Br and minimum Hcj.
 Magnets can be supplied thermal stabilized or magnetically calibrated to customer specifications.
 Additional grades are available, Please contact the factory for information.